

## TECHNICAL DATA SHEET

 **Starweld 499**

**AC / DC+**


### HARDFACING

#### Description :

Tubular electrode with high tungsten carbide content designed to combat extremely severe abrasion and moderate impact. Starweld 499 is easy to apply to steel, stainless steel and cast-iron parts.

#### Characteristics :

- Very performant at low amperage
- All-positions
- Stable arc and spatter-free
- Highly alloyed deposit
- High deposit rate
- 60 % tungsten carbide content



#### Mechanical properties :

- Polarity AC / DC +
- Hardness (matrix) : 55 - 60 HRC
- Tungsten carbides hardness : 2000 – 2500 HV

+ **Diameter**  
+ **Amperage**

3.2 mm  
90 - 120 A

4.0 mm  
120 - 160 A

#### Applications :

Augers, blades, rakes, scrapers, mixer paddles, earth augers, construction equipment, etc.

**1 800 361 9097**

 **Starweld**